

Blockout PE Ruka		Technical info	
Composition		Polyester 66% - PUR 34%	
Openness factor	NBN EN 410	0.00%	
Weight	NF EN 12127	310.00 g/m ²	
Thickness	ISO 5084	0.25 mm	
Color fastness to artificial light	ISO 105 B02	front 6, back >7	
Roll length		30 m	
Fire classification			
└ Europe	UNE-EN 13501-1:2007	C-s3, d0	
└ France	NF P92-503	M1	
└ Italy	UNI 9177	Class 1	
└ Germany	DIN 4102	B1	
└ UK	BS 5867	C	
└ USA	NFPA 701	FR	
Tear strength	ISO 4674-1 method 2		
└ Original		WARP 1.65 daN	WEFT 3.10 daN
└ After climatic chamber -30°C		WARP 1.50 daN	WEFT 2.90 daN
└ After climatic chamber +70°C		WARP 1.65 daN	WEFT 3.20 daN
Elongation up to break	ISO 1421		
└ Original		WARP 25.60 %	WEFT 30.00 %
└ After color fastness to artificial light		WARP 23.50 %	WEFT 30.00 %
└ After climatic chamber -30°C		WARP 29.50 %	WEFT 33.00 %
└ After climatic chamber +70°C		WARP 28.00 %	WEFT 28.50 %
Breaking strength	ISO 1421		
└ Original		WARP 125.00 daN/5cm	WEFT 165.00 daN/5cm
└ After color fastness to artificial light		WARP 120.00 daN/5cm	WEFT 160.00 daN/5cm
└ After climatic chamber -30°C		WARP 135.00 daN/5cm	WEFT 170.00 daN/5cm
└ After climatic chamber +70°C		WARP 130.00 daN/5cm	WEFT 160.00 daN/5cm