

Blockout PE Ruka		Technical info	
<b>Composition</b>		Polyester 66% - PUR 34%	
<b>Openness factor</b>	NBN EN 410	0.00%	
<b>Weight</b>	NF EN 12127	310.00 g/m <sup>2</sup>	
<b>Thickness</b>	ISO 5084	0.25 mm	
<b>Color fastness to artificial light</b>	ISO 105 B02	front 6, back >7	
<b>Roll length</b>		30 m	
<b>Fire classification</b>			
└ Europe	UNE-EN 13501-1:2007	C-s3, d0	
└ France	NF P92-503	M1	
└ Italy	UNI 9177	Class 1	
└ Germany	DIN 4102	B1	
└ UK	BS 5867	C	
└ USA	NFPA 701	FR	
<b>Tear strength</b>	ISO 4674-1 method 2		
└ Original		WARP 1.65 daN	WEFT 3.10 daN
└ After climatic chamber -30°C		WARP 1.50 daN	WEFT 2.90 daN
└ After climatic chamber +70°C		WARP 1.65 daN	WEFT 3.20 daN
<b>Elongation up to break</b>	ISO 1421		
└ Original		WARP 25.60 %	WEFT 30.00 %
└ After color fastness to artificial light		WARP 23.50 %	WEFT 30.00 %
└ After climatic chamber -30°C		WARP 29.50 %	WEFT 33.00 %
└ After climatic chamber +70°C		WARP 28.00 %	WEFT 28.50 %
<b>Breaking strength</b>	ISO 1421		
└ Original		WARP 125.00 daN/5cm	WEFT 165.00 daN/5cm
└ After color fastness to artificial light		WARP 120.00 daN/5cm	WEFT 160.00 daN/5cm
└ After climatic chamber -30°C		WARP 135.00 daN/5cm	WEFT 170.00 daN/5cm
└ After climatic chamber +70°C		WARP 130.00 daN/5cm	WEFT 160.00 daN/5cm