

Déco N203 Blockout		Technical info	
Composition		Déco N203 flock laminiert	
Openness factor	NBN EN 410	0.00%	
Weight	NF EN 12127	700.00 g/m ²	
Thickness	ISO 5084	0.65 mm	
Density	ISO 7211/2	WARP 22.00 yarn/cm	WEFT 20.00 yarn/cm
Color fastness to artificial light	ISO 105 B02	>7	
Roll length		30 m	
Cleaning		Mit Seifenwasser	
Confection		By heat, high frequency or ultrasonic welding	
Fire classification		awaiting results	
└ Europe	UNE-EN 13501-1:2007	awaiting results	
└ France	NF P92-503	M2	
└ Italy	UNI 9177	Class 1	
└ Germany	DIN 4102	B2	
└ UK	BS 5867	C	
└ USA	NFPA 701	FR	
Tear strength	ISO 4674-1 methode 2		
└ Original		WARP 2.90 daN	WEFT 3.10 daN
└ After climatic chamber -30°C		WARP 2.40 daN	WEFT 2.90 daN
└ After climatic chamber +70°C		WARP 2.70 daN	WEFT 3.40 daN
Elongation up to break	ISO 1421		
└ Original		WARP 7.20 %	WEFT 3.50 %
└ After color fastness to artificial light		WARP 6.10 %	WEFT 2.90 %
└ After climatic chamber -30°C		WARP 6.30 %	WEFT 2.80 %
└ After climatic chamber +70°C		WARP 5.10 %	WEFT 1.40 %
Breaking strength	ISO 1421		
└ Original		WARP 185.00 daN/5cm	WEFT 200.00 daN/5cm
└ After color fastness to artificial light		WARP 170.00 daN/5cm	WEFT 200.00 daN/5cm
└ After climatic chamber -30°C		WARP 125.00 daN/5cm	WEFT 160.00 daN/5cm
└ After climatic chamber +70°C		WARP 110.00 daN/5cm	WEFT 90.00 daN/5cm