

| Déco N203 Blockout | | Technical info | |
|--|----------------------|---|---------------------|
| Composition | | Déco N203 flock laminated | |
| Openness factor | NBN EN 410 | 0.00% | |
| Weight | NF EN 12127 | 700.00 g/m ² | |
| Thickness | ISO 5084 | 0.65 mm | |
| Density | ISO 7211/2 | WARP 22.00 yarn/cm | WEFT 20.00 yarn/cm |
| Color fastness to artificial light | ISO 105 B02 | >7 | |
| Roll length | | 30 m | |
| Cleaning | | With soapy water | |
| Confection | | By heat, high frequency or ultrasonic welding | |
| Fire classification | | | |
| └ Europe | UNE-EN 13501-1:2007 | C-s3, d0 | |
| └ France | NF P92-503 | M1 | |
| └ Italy | UNI 9177 | Class 1 | |
| └ Germany | DIN 4102 | B1 | |
| └ UK | BS 5867 | C | |
| └ USA | NFPA 701 | FR | |
| Tear strength | ISO 4674-1 methode 2 | | |
| └ Original | | WARP 2.90 daN | WEFT 3.10 daN |
| └ After climatic chamber -30°C | | WARP 2.40 daN | WEFT 2.90 daN |
| └ After climatic chamber +70°C | | WARP 2.70 daN | WEFT 3.40 daN |
| Elongation up to break | ISO 1421 | | |
| └ Original | | WARP 7.20 % | WEFT 3.50 % |
| └ After color fastness to artificial light | | WARP 6.10 % | WEFT 2.90 % |
| └ After climatic chamber -30°C | | WARP 6.30 % | WEFT 2.80 % |
| └ After climatic chamber +70°C | | WARP 5.10 % | WEFT 1.40 % |
| Breaking strength | ISO 1421 | | |
| └ Original | | WARP 185.00 daN/5cm | WEFT 200.00 daN/5cm |
| └ After color fastness to artificial light | | WARP 170.00 daN/5cm | WEFT 200.00 daN/5cm |
| └ After climatic chamber -30°C | | WARP 125.00 daN/5cm | WEFT 160.00 daN/5cm |
| └ After climatic chamber +70°C | | WARP 110.00 daN/5cm | WEFT 90.00 daN/5cm |