

Opac 400 Classic		Technical info	
<b>Composition</b>		Fabric of vinyl laminated glassfibre	
<b>Openness factor</b>	NBN EN 410	0.00%	
<b>Weight</b>	NF EN 12127	432.00 g/m <sup>2</sup>	
<b>Thickness</b>	ISO 5084	0.34 mm	
<b>Color fastness to artificial light</b>	ISO 105 B02	7	
<b>Roll length</b>		30 m	
<b>Cleaning</b>		With soapy water	
<b>Confection</b>		By heat, high frequency or ultrasonic welding	
<b>Fire classification</b>			
└ France	NF P92-503	M2	
└ Italy	UNI 9177	Class 1	
└ Spain	UNE 13773	Clase 1	
<b>Tear strength</b>	ISO 4674-1 method 2		
└ Original		WARP 6.90 daN	WEFT 6.30 daN
└ After climatic chamber -30°C		WARP 5.60 daN	WEFT 5.30 daN
└ After climatic chamber +70°C		WARP 6.70 daN	WEFT 5.30 daN
<b>Elongation up to break</b>	ISO 1421		
└ Original		WARP 3.90 %	WEFT 3.74 %
└ After color fastness to artificial light		WARP 3.17 %	WEFT 3.26 %
└ After climatic chamber -30°C		WARP 3.48 %	WEFT 4.24 %
└ After climatic chamber +70°C		WARP 4.32 %	WEFT 4.16 %
<b>Breaking strength</b>	ISO 1421		
└ Original		WARP 168.60 daN/5cm	WEFT 201.30 daN/5cm
└ After color fastness to artificial light		WARP 94.10 daN/5cm	WEFT 105.50 daN/5cm
└ After climatic chamber -30°C		WARP 151.70 daN/5cm	WEFT 221.10 daN/5cm
└ After climatic chamber +70°C		WARP 182.80 daN/5cm	WEFT 223.90 daN/5cm