

Opac 400 Classic		Technical info	
Composition		Fabric of vinyl laminated glassfibre	
Openness factor	NBN EN 410	0.00%	
Weight	NF EN 12127	432.00 g/m ²	
Thickness	ISO 5084	0.34 mm	
Color fastness to artificial light	ISO 105 B02	7	
Roll length		30 m	
Cleaning		With soapy water	
Confection		By heat, high frequency or ultrasonic welding	
Fire classification			
└ Europe	UNE-EN 13501-1:2007	C-s3, d0	
└ France	NF P92-503	M1	
└ Italy	UNI 9177	Class 1	
└ Germany	DIN 4102	B1	
└ UK	BS 5867	C	
└ USA	NFPA 701	FR	
Tear strength	ISO 4674-1 method 2		
└ Original		WARP 6.90 daN	WEFT 6.30 daN
└ After climatic chamber -30°C		WARP 5.60 daN	WEFT 5.30 daN
└ After climatic chamber +70°C		WARP 6.70 daN	WEFT 5.30 daN
Elongation up to break	ISO 1421		
└ Original		WARP 3.90 %	WEFT 3.74 %
└ After color fastness to artificial light		WARP 3.17 %	WEFT 3.26 %
└ After climatic chamber -30°C		WARP 3.48 %	WEFT 4.24 %
└ After climatic chamber +70°C		WARP 4.32 %	WEFT 4.16 %
Breaking strength	ISO 1421		
└ Original		WARP 168.60 daN/5cm	WEFT 201.30 daN/5cm
└ After color fastness to artificial light		WARP 94.10 daN/5cm	WEFT 105.50 daN/5cm
└ After climatic chamber -30°C		WARP 151.70 daN/5cm	WEFT 221.10 daN/5cm
└ After climatic chamber +70°C		WARP 182.80 daN/5cm	WEFT 223.90 daN/5cm