

Serge 600 Blockout		Technical info	
<b>Composition</b>		Serge 600 laminiert mit einer PVC-folie	
<b>Openness factor</b>	NBN EN 410	0.00%	
<b>Weight</b>	NF EN 12127	800.00 g/m <sup>2</sup>	
<b>Thickness</b>	ISO 5084	0.56 mm	
<b>Density</b>	ISO 7211/2	WARP 18.00 yarn/cm	WEFT 14.00 yarn/cm
<b>Color fastness to artificial light</b>	ISO 105 B02	>7	
<b>Roll length</b>		50 m	
<b>Cleaning</b>		Mit Seifenwasser	
<b>Confection</b>		By heat, high frequency or ultrasonic welding	
<b>Fire classification</b>			
└ Europe	UNE-EN 13501-1:2007	C-s3, d0	
└ France	NF P92-503	M1	
└ Italy	UNI 9177	Class 1	
└ Germany	DIN 4102	B1	
└ UK	BS 5867	C	
└ USA	NFPA 701	FR	
<b>Tear strength</b>	ISO 4674-1 methode 2		
└ Original		WARP 9.70 daN	WEFT 8.90 daN
└ After climatic chamber -30°C		WARP 9.60 daN	WEFT 9.00 daN
└ After climatic chamber +70°C		WARP 10.20 daN	WEFT 9.20 daN
<b>Elongation up to break</b>	ISO 1421		
└ Original		WARP 3.40 %	WEFT 3.50 %
└ After color fastness to artificial light		WARP 3.60 %	WEFT 4.00 %
└ After climatic chamber -30°C		WARP 3.60 %	WEFT 3.70 %
└ After climatic chamber +70°C		WARP 3.90 %	WEFT 3.90 %
<b>Breaking strength</b>	ISO 1421		
└ Original		WARP 310.00 daN/5cm	WEFT 230.00 daN/5cm
└ After color fastness to artificial light		WARP 310.00 daN/5cm	WEFT 240.00 daN/5cm
└ After climatic chamber -30°C		WARP 300.00 daN/5cm	WEFT 210.00 daN/5cm
└ After climatic chamber +70°C		WARP 305.00 daN/5cm	WEFT 240.00 daN/5cm