

Verso 1		Technical info	
Composition		Fibreglass 36% - PVC 64%	
Openness factor	NF EN 12127	1.00%	
Weight	NF EN 12127	465.00 g/m ²	
Thickness	ISO 5084	0.60 mm	
Density	ISO 7211/2	WARP 24.00 yarn/cm	WEFT 25.00 yarn/cm
Color fastness to artificial light	ISO 105 B02	>7	
Roll length		30 m	
Cleaning		With soapy water	
Confection		By heat, high frequency or ultrasonic welding	
Fire classification			
└ Europe	UNE-EN 13501-1:2007	C-s3, d0	
└ France	NF P92-503	M1	
└ Italy	UNI 9177	Class 1	
└ Germany	DIN 4102	B1	
└ UK	BS 5867	C	
└ USA	NFPA 701	FR	
Tear strength	ISO 4674-1 methode 2		
└ Original		WARP 2.20 daN	WEFT 2.40 daN
└ After climatic chamber -30°C		WARP 2.05 daN	WEFT 2.10 daN
└ After climatic chamber +70°C		WARP 2.30 daN	WEFT 2.70 daN
Elongation up to break	ISO 1421		
└ Original		WARP 2.85 %	WEFT 2.40 %
└ After color fastness to artificial light		WARP 3.10 %	WEFT 2.90 %
└ After climatic chamber -30°C		WARP 2.10 %	WEFT 2.60 %
└ After climatic chamber +70°C		WARP 2.00 %	WEFT 2.70 %
Breaking strength	ISO 1421		
└ Original		WARP 185.00 daN/5cm	WEFT 130.00 daN/5cm
└ After color fastness to artificial light		WARP 175.00 daN/5cm	WEFT 140.00 daN/5cm
└ After climatic chamber -30°C		WARP 115.00 daN/5cm	WEFT 120.00 daN/5cm
└ After climatic chamber +70°C		WARP 100.00 daN/5cm	WEFT 100.00 daN/5cm