

Déco N203 (end 31.12.2024)		Technical info
Composition		Fibreglass 36% - PVC 64%
Openness factor	NBN EN 410	3.00%
Weight	NF EN 12127	435.00 g/m ²
Thickness	ISO 5084	0.45 mm
Density	ISO 7211/2	WARP 22.00 yarn/cm WEFT 20.00 yarn/cm
Color fastness to artificial light	ISO 105 B02	>7
Roll length		30 m
Cleaning		With soapy water
Confection		By heat, high frequency or ultrasonic welding
Fire classification		
└ Europe	UNE-EN 13501-1:2007	C-s3,d0
└ France	NF P92-503	M2
└ Italy	UNI 9177	Class 1
└ Germany	DIN 4102	B2
└ UK	BS 5867	C
└ USA	NFPA 701	FR
└ Spain	UNE 13773	Clase 1
Tear strength	ISO 4674-1 methode 2	
└ Original		WARP 3.30 daN WEFT 3.65 daN
└ After climatic chamber -30°C		WARP 3.00 daN WEFT 3.80 daN
└ After climatic chamber +70°C		WARP 3.10 daN WEFT 3.60 daN
Elongation up to break	ISO 1421	
└ Original		WARP 8.80 % WEFT 2.80 %
└ After color fastness to artificial light		WARP 8.70 % WEFT 2.70 %
└ After climatic chamber -30°C		WARP 8.60 % WEFT 1.80 %
└ After climatic chamber +70°C		WARP 8.90 % WEFT 1.90 %
Breaking strength	ISO 1421	
└ Original		WARP 125.00 daN/5cm WEFT 175.00 daN/5cm
└ After color fastness to artificial light		WARP 120.00 daN/5cm WEFT 185.00 daN/5cm
└ After climatic chamber -30°C		WARP 120.00 daN/5cm WEFT 140.00 daN/5cm
└ After climatic chamber +70°C		WARP 130.00 daN/5cm WEFT 125.00 daN/5cm