

Ulterio 3%		Technical info
Composition		100% Recycled PET bottles
Openness factor	NBN EN 410	3.00%
Weight	NF EN 12127	223.00 g/m ²
Thickness	ISO 5084	0.53 mm
Density	ISO 7211/2	WARP 21.00 yarn/cm WEFT 18.00 yarn/cm
Color fastness to artificial light	ISO 105 B02	> 7
Roll length		30 m
Cleaning		With soapy water
Confection		By heat, high frequency or ultrasonic welding
Fire classification		
└ Europe	UNE-EN 13501-1:2007	C-s3, d0
└ France	NF P92-503	M1
└ Italy	UNI 9177	Class 1
└ Germany	DIN 4102	B1
└ UK	BS 5867	C
└ USA	NFPA 701	FR
Tear strength	ISO 4674-1 methode 2	
└ Original		WARP 5.20 daN WEFT 6.80 daN
└ After climatic chamber -30°C		WARP 5.00 daN WEFT 6.20 daN
└ After climatic chamber +70°C		WARP 5.20 daN WEFT 6.70 daN
Elongation up to break	ISO 1421	
└ Original		WARP 36.00 % WEFT 33.50 %
Breaking strength	ISO 1421	
└ Original		WARP 160.00 daN/5cm WEFT 135.00 daN/5cm