

Zilario 3%		Technical info	
<b>Composition</b>		100% Recyclete Plastikflaschen	
<b>Openness factor</b>	NBN EN 410	3.00%	
<b>Weight</b>	NF EN 12127	226.00 g/m <sup>2</sup>	
<b>Thickness</b>	ISO 5084	0.46 mm	
<b>Density</b>	ISO 7211/2	WARP 21.00 yarn/cm	WEFT 18.00 yarn/cm
<b>Color fastness to artificial light</b>	ISO 105 B02	>7	
<b>Roll length</b>		30 m	
<b>Cleaning</b>		Mit Seifenwasser	
<b>Confection</b>		By heat or ultrasonic welding with an extra hot glue tape	
<b>Fire classification</b>			
└ Europe	UNE-EN 13501-1:2007	C-s3, d0	
└ France	NF P92-503	M1	
└ Italy	UNI 9177		
└ Germany	DIN 4102	B1	
└ UK	BS 5867		
└ USA	NFPA 701		
<b>Tear strength</b>	ISO 4674-1 methode 2		
└ Original		WARP 5.20 daN	WEFT 6.80 daN
└ After climatic chamber -30°C		WARP 5.00 daN	WEFT 6.20 daN
└ After climatic chamber +70°C		WARP 5.20 daN	WEFT 6.70 daN
<b>Elongation up to break</b>	ISO 1421		
└ Original		WARP 36.00 %	WEFT 33.50 %
<b>Breaking strength</b>	ISO 1421		
└ Original		WARP 160.00 daN/5cm	WEFT 135.00 daN/5cm