

Zilario 3%		Technical info	
Composition		100% Recycled PET bottles	
Openness factor	NBN EN 410	3.00%	
Weight	NF EN 12127	226.00 g/m ²	
Thickness	ISO 5084	0.46 mm	
Density	ISO 7211/2	WARP 21.00 yarn/cm	WEFT 18.00 yarn/cm
Color fastness to artificial light	ISO 105 B02	>7	
Roll length		30 m	
Cleaning		With soapy water	
Confection		By heat or ultrasonic welding with an extra hot glue tape	
Fire classification			
└ Europe	UNE-EN 13501-1:2007	C-s3, d0	
└ France	NF P92-503	M1	
└ Italy	UNI 9177		
└ Germany	DIN 4102	B1	
└ UK	BS 5867		
└ USA	NFPA 701		
Tear strength	ISO 4674-1 methode 2		
└ Original		WARP 5.20 daN	WEFT 6.80 daN
└ After climatic chamber -30°C		WARP 5.00 daN	WEFT 6.20 daN
└ After climatic chamber +70°C		WARP 5.20 daN	WEFT 6.70 daN
Elongation up to break	ISO 1421		
└ Original		WARP 36.00 %	WEFT 33.50 %
Breaking strength	ISO 1421		
└ Original		WARP 160.00 daN/5cm	WEFT 135.00 daN/5cm