

Serge 10%		Technical info	
<b>Composition</b>		Glassfibre 42% - PVC 58%	
<b>Openness factor</b>	NBN EN 410	10.00%	
<b>Weight</b>	NF EN 12127	490.00 g/m <sup>2</sup>	
<b>Thickness</b>	ISO 5084	0.83 mm	
<b>Density</b>	ISO 2286-3	WARP 18.00 yarn/cm	WEFT 12.00 yarn/cm
<b>Color fastness to artificial light</b>	ISO 105 B02	>7	
<b>Color fastness to artificial weathering</b>	ISO 105 B04	>7	
<b>Roll length</b>		50 m	
<b>Cleaning</b>		With soapy water	
<b>Confection</b>		By heat, high frequency or ultrasonic welding	
<b>Fire classification</b>			
└ Europe	UNE-EN 13501-1:2007		
└ France	NF P92-503	<b>M1</b>	
└ Italy	UNI 9177	<b>Class 1</b>	
└ Germany	DIN 4102	<b>B1</b>	
└ UK	BS 5867	<b>C</b>	
└ USA	NFPA 701	<b>FR</b>	
<b>Tear strength</b>	ISO 4674-1 method 2		
└ Original		WARP 9.60 daN	WEFT 7.60 daN
└ After climatic chamber -30°C		WARP 8.60 daN	WEFT 7.10 daN
└ After climatic chamber +70°C		WARP 8.80 daN	WEFT 7.00 daN
<b>Elongation up to break</b>	ISO 1421		
└ Original		WARP 5.20 %	WEFT 4.90 %
└ After colour fastness to artificial weathering		WARP 5.80 %	WEFT 5.00 %
└ After color fastness to artificial light		WARP 6.70 %	WEFT 5.20 %
└ After climatic chamber -30°C		WARP 5.00 %	WEFT 4.80 %
└ After climatic chamber +70°C		WARP 4.80 %	WEFT 4.20 %
<b>Breaking strength</b>	ISO 1421		
└ Original		WARP 312.00 daN/5cm	WEFT 200.00 daN/5cm
└ After colour fastness to artificial weathering		WARP 289.00 daN/5cm	WEFT 190.00 daN/5cm
└ After color fastness to artificial light		WARP 289.00 daN/5cm	WEFT 185.00 daN/5cm
└ After climatic chamber -30°C		WARP 271.00 daN/5cm	WEFT 174.00 daN/5cm
└ After climatic chamber +70°C		WARP 217.00 daN/5cm	WEFT 139.00 daN/5cm