

Serge 1%		Technical info	
Composition		Glassfibre 42% - PVC 58%	
Openness factor	NBN EN 410	1.00%	
Weight	NF EN 12127	620.00 g/m ²	
Thickness	ISO 5084	0.80 mm	
Density	ISO 7211/2	WARP 20.00 yarn/cm	WEFT 18.00 yarn/cm
Color fastness to artificial light	ISO 105 B02	>7	
Color fastness to artificial weathering	ISO 105 B04	>7	
Air permeability	ISO 9237	497.00l/m ² /s	
Roll length		30 m	
Cleaning		With soapy water	
Confection		By heat, high frequency or ultrasonic welding	
Fire classification			
└ Europe	UNE-EN 13501-1:2007	C-s3, d0	
└ France	NF P92-503	M1	
└ Italy	UNI 9177	Class 1	
└ Germany	DIN 4102	B1	
└ UK	BS 5867	C	
└ USA	NFPA 701	FR	
Tear strength	ISO 4674-1 methode 2		
└ Original		WARP 5.90 daN	WEFT 6.20 daN
└ After climatic chamber -30°C		WARP 6.00 daN	WEFT 6.20 daN
└ After climatic chamber +70°C		WARP 5.30 daN	WEFT 5.80 daN
Elongation up to break	ISO 1421		
└ Original		WARP 4.70 %	WEFT 3.80 %
└ After colour fastness to artificial weathering		WARP 4.70 %	WEFT 3.30 %
└ After climatic chamber -30°C		WARP 4.80 %	WEFT 3.90 %
└ After climatic chamber +70°C		WARP 5.00 %	WEFT 3.70 %
Breaking strength	ISO 1421		
└ Original		WARP 321.00 daN/5cm	WEFT 277.00 daN/5cm
└ After colour fastness to artificial weathering		WARP 225.00 daN/5cm	WEFT 216.00 daN/5cm
└ After climatic chamber -30°C		WARP 236.00 daN/5cm	WEFT 279.00 daN/5cm
└ After climatic chamber +70°C		WARP 251.00 daN/5cm	WEFT 266.00 daN/5cm