

Serge 600 Blockout Lunar		Technical info
Composition		Fibreglass 33% - PVC 47% - PVC laminate 20%
Openness factor	NBN EN 410	0.00%
Weight	NF EN 12127	678.00 g/m ²
Thickness	ISO 5084	0.73 mm
Density	ISO 7211/2	WARP 18.00 yarn/cm WEFT 14.00 yarn/cm
Color fastness to artificial weathering	ISO 105 B04	>7
Air permeability	ISO 9237	0.0
Roll length		30 m
Cleaning		With soapy water
Confection		By heat, high frequency or ultrasonic welding
Fire classification		
└ Germany	DIN 4102	awaiting test results
└ UK	BS 5867	awaiting test results
└ USA	NFPA 701	awaiting test results
└ France	NF P92-503	M2
└ Italy	UNI 9177	Class 1
Tear strength	ISO 4674-1 methode 2	
└ Original		WARP 8.50 daN WEFT 9.00 daN
└ After climatic chamber -30°C		WARP 8.40 daN WEFT 9.30 daN
└ After climatic chamber +70°C		WARP 8.80 daN WEFT 9.30 daN
Elongation up to break	ISO 1421	
└ Original		WARP 6.40 % WEFT 7.30 %
└ After colour fastness to artificial weathering		WARP 6.50 % WEFT 7.00 %
└ After climatic chamber -30°C		WARP 6.20 % WEFT 6.90 %
└ After climatic chamber +70°C		WARP 6.40 % WEFT 6.70 %
Breaking strength	ISO 1421	
└ Original		WARP 224.20 daN/5cm WEFT 176.60 daN/5cm
└ After colour fastness to artificial weathering		WARP 214.20 daN/5cm WEFT 168.00 daN/5cm
└ After climatic chamber -30°C		WARP 222.40 daN/5cm WEFT 162.60 daN/5cm
└ After climatic chamber +70°C		WARP 213.90 daN/5cm WEFT 161.60 daN/5cm
Recommendations		To be used in sunscreensystems with Zipscreens.