

Serge 600 Blockout Lunar		Technical info
<b>Composition</b>		Fibreglass 33% - PVC 47% - PVC laminate 20%
<b>Openness factor</b>	NBN EN 410	0.00%
<b>Weight</b>	NF EN 12127	678.00 g/m <sup>2</sup>
<b>Thickness</b>	ISO 5084	0.73 mm
<b>Density</b>	ISO 7211/2	WARP 18.00 yarn/cm      WEFT 14.00 yarn/cm
<b>Color fastness to artificial weathering</b>	ISO 105 B04	>7
<b>Air permeability</b>	ISO 9237	0.0
<b>Roll length</b>		30 m
<b>Cleaning</b>		With soapy water
<b>Confection</b>		By heat, high frequency or ultrasonic welding
<b>Fire classification</b>		
└ Germany	DIN 4102	awaiting test results
└ UK	BS 5867	awaiting test results
└ USA	NFPA 701	awaiting test results
└ France	NF P92-503	M1
└ Italy	UNI 9177	Class 1
<b>Tear strength</b>	ISO 4674-1 methode 2	
└ Original		WARP 8.50 daN      WEFT 9.00 daN
└ After climatic chamber -30°C		WARP 8.40 daN      WEFT 9.30 daN
└ After climatic chamber +70°C		WARP 8.80 daN      WEFT 9.30 daN
<b>Elongation up to break</b>	ISO 1421	
└ Original		WARP 6.40 %      WEFT 7.30 %
└ After colour fastness to artificial weathering		WARP 6.50 %      WEFT 7.00 %
└ After climatic chamber -30°C		WARP 6.20 %      WEFT 6.90 %
└ After climatic chamber +70°C		WARP 6.40 %      WEFT 6.70 %
<b>Breaking strength</b>	ISO 1421	
└ Original		WARP 224.20 daN/5cm      WEFT 176.60 daN/5cm
└ After colour fastness to artificial weathering		WARP 214.20 daN/5cm      WEFT 168.00 daN/5cm
└ After climatic chamber -30°C		WARP 222.40 daN/5cm      WEFT 162.60 daN/5cm
└ After climatic chamber +70°C		WARP 213.90 daN/5cm      WEFT 161.60 daN/5cm
<b>Recommendations</b>		To be used in sunscreensystems with Zipscreens.