

Serge 600 OUT in the jungle		Technical info
Composition		Fibreglass 42% - PVC 58%
Openness factor	NBN EN 410	5.00%
Weight	NF EN 12127	525.00 g/m ²
Thickness	ISO 5084	0.74 mm
Density	ISO 7211/2	WARP 18.00 yarn/cm WEFT 14.00 yarn/cm
Color fastness to artificial light	ISO 105 B02	>7
Color fastness to artificial weathering	ISO 105 B04	>7
Air permeability	ISO 9237	580.00 l/m ² /s
Roll length		50 m / 30 m for all widths > 270 cm
Cleaning		With soapy water
Confection		By heat, high frequency or ultrasonic welding
Fire classification		
└ Europe	UNE-EN 13501-1:2007	C-s3, d0
└ France	NF P92-503	M1
└ Italy	UNI 9177	Class 1
└ Germany	DIN 4102	B2
└ UK	BS 5867	C
└ USA	NFPA 701	FR
Tear strength	ISO 4674-1 methode 2	
└ Original		WARP 8.50 daN WEFT 7.50 daN
└ After climatic chamber -30°C		WARP 7.80 daN WEFT 7.50 daN
└ After climatic chamber +70°C		WARP 8.20 daN WEFT 7.20 daN
Elongation up to break	ISO 1421	
└ Original		WARP 3.10 % WEFT 2.75 %
└ After color fastness to artificial light		WARP 4.00 % WEFT 2.90 %
└ After colour fastness to artificial weathering		WARP 3.50 % WEFT 2.80 %
└ After climatic chamber -30°C		WARP 3.00 % WEFT 2.50 %
└ After climatic chamber +70°C		WARP 2.85 % WEFT 2.50 %
Breaking strength	ISO 1421	
└ Original		WARP 260.00 daN/5cm WEFT 225.00 daN/5cm
└ After color fastness to artificial light		WARP 240.00 daN/5cm WEFT 220.00 daN/5cm
└ After colour fastness to artificial weathering		WARP 240.00 daN/5cm WEFT 225.00 daN/5cm
└ After climatic chamber -30°C		WARP 225.00 daN/5cm WEFT 200.00 daN/5cm
└ After climatic chamber +70°C		WARP 180.00 daN/5cm WEFT 185.00 daN/5cm