

Office 180		Technical info	
Composition		Polyester 100%	
Openness factor	NBN EN 14500-B1	6.00%	
Weight	NF EN 12127	160.00 g/m ²	
Thickness	ISO 2286-3	0.35 mm	
Density	ISO 7211/	WARP 33.00 yarn/cm	WEFT 24.00 yarn/cm
Color fastness to artificial light	ISO 105 B02	>6	
Roll length		40 m	
Cleaning		Mit Seifenwasser	
Fire classification			
└ Europe	UNE-EN 13501-1:2007	C-s3, d0	
└ France	NF P92-503	M2	
└ Germany	DIN 4102	B1	
└ Spain	UNE EN 13773-2003	Clase 1	
Tear strength	ISO 4674-1B		
└ Original		WARP 2.00 daN	WEFT 0.90 daN
└ After climatic chamber -30°C		WARP 1.70 daN	WEFT 0.90 daN
Elongation up to break	ISO 1421		
└ Original		WARP 16.80 %	WEFT 14.40 %
└ After climatic chamber -30°C		WARP 18.40 %	WEFT 14.30 %
└ After climatic chamber +70°C		WARP 19.30 %	WEFT 14.60 %
Breaking strength	ISO 1421		
└ Original		WARP 19.70 daN/5cm	WEFT 87.50 daN/5cm
└ After climatic chamber -30°C		WARP 21.80 daN/5cm	WEFT 89.40 daN/5cm
└ After climatic chamber +70°C		WARP 1.80 daN/5cm	WEFT 0.80 daN/5cm
└ After climatic chamber +70°C		WARP 23.30 daN/5cm	WEFT 86.40 daN/5cm