

| Office 180 | | Technical info | |
|---|---------------------|-------------------------|--------------------|
| Composition | | Polyester 100% | |
| Openness factor | NBN EN 14500-B1 | 6.00% | |
| Weight | NF EN 12127 | 160.00 g/m ² | |
| Thickness | ISO 2286-3 | 0.35 mm | |
| Density | ISO 7211/ | WARP 33.00 yarn/cm | WEFT 24.00 yarn/cm |
| Color fastness to artificial light | ISO 105 B02 | >6 | |
| Roll length | | 40 m | |
| Cleaning | | With soapy water | |
| Fire classification | | | |
| └ Europe | UNE-EN 13501-1:2007 | C-s3, d0 | |
| └ France | NF P92-503 | M2 | |
| └ Germany | DIN 4102 | B1 | |
| └ Spain | UNE EN 13773-2003 | Clase 1 | |
| Tear strength | ISO 4674-1B | | |
| └ Original | | WARP 2.00 daN | WEFT 0.90 daN |
| └ After climatic chamber -30°C | | WARP 1.70 daN | WEFT 0.90 daN |
| Elongation up to break | ISO 1421 | | |
| └ Original | | WARP 16.80 % | WEFT 14.40 % |
| └ After climatic chamber -30°C | | WARP 18.40 % | WEFT 14.30 % |
| └ After climatic chamber +70°C | | WARP 19.30 % | WEFT 14.60 % |
| Breaking strength | ISO 1421 | | |
| └ Original | | WARP 19.70 daN/5cm | WEFT 87.50 daN/5cm |
| └ After climatic chamber -30°C | | WARP 21.80 daN/5cm | WEFT 89.40 daN/5cm |
| └ After climatic chamber +70°C | | WARP 1.80 daN/5cm | WEFT 0.80 daN/5cm |
| └ After climatic chamber +70°C | | WARP 23.30 daN/5cm | WEFT 86.40 daN/5cm |