

Bicolor		Technical info
Composition		Polyester 16% - PVC 84%
Openness factor	NBN EN 14500-B1	5.00%
Weight	NF EN 12127	440.00 g/m ²
Thickness	ISO 2286-3	0.62 mm
Density	ISO 7211/2	WARP 19.00 yarn/cm WEFT 19.00 yarn/cm
Color fastness to artificial light	ISO 4674-1B	>7
Roll length		30 m
Cleaning		With soapy water
Confection		Confection cut: by heat, high frequency or ultrasonic welding by reinforce tape / Confection welding: cruch cut, ultrasonic, laser
Fire classification		
└ Europe	UNE-EN 13501-1:2007	C-s3, d0
└ France	NF P92-503	M2
└ Spain	UNE EN 13773-2003	Clase 1
Tear strength	ISO 1421	
└ Original		WARP 2.00 daN WEFT 4.10 daN
└ After climatic chamber -30°C		WARP 2.00 daN WEFT 3.80 daN
└ After climatic chamber +70°C		WARP 23.84 daN WEFT 15.37 daN
Elongation up to break	ISO 1421	
└ Original		WARP 21.83 % WEFT 17.43 %
└ After climatic chamber -30°C		WARP 20.90 % WEFT 13.43 %
└ After climatic chamber +70°C		WARP 23.84 % WEFT 15.37 %
Breaking strength	ISO 1421	
└ Original		WARP 80.20 daN/5cm WEFT 64.50 daN/5cm
└ After climatic chamber -30°C		WARP 81.90 daN/5cm WEFT 66.20 daN/5cm
└ After climatic chamber +70°C		WARP 79.40 daN/5cm WEFT 64.80 daN/5cm