

Classic		Technical info
Composition		Polyester 16% - PVC 84%
Openness factor	NBN EN 14500-B1	5.00%
Weight	NF EN 12127	530.00 g/m ²
Thickness	ISO 2286-3	0.77 mm
Density	ISO 7211/2	WARP 15.00 yarn/cm WEFT 15.00 yarn/cm
Color fastness to artificial light	ISO 105 B02	>7
Roll length		30 m
Cleaning		With soapy water
Confection		Confection cut: by heat, high frequency or ultrasonic welding by reinforce tape / Confection welding: cruch cut, ultrasonic, laser
Fire classification		
└ Europe	UNE-EN 13501-1:2007	C-s3, d0
└ France	NF P92-503	M2
└ Spain	UNE EN 13773-2003	Clase 1
Tear strength	ISO 1421	
└ Original		WARP 9.20 daN WEFT 5.10 daN
└ After climatic chamber -30°C		WARP 8.80 daN WEFT 5.00 daN
└ After climatic chamber +70°C		WARP 9.10 daN WEFT 5.50 daN
Elongation up to break	ISO 1421	
└ Original		WARP 21.33 % WEFT 32.94 %
└ After climatic chamber -30°C		WARP 20.26 % WEFT 31.59 %
└ After climatic chamber +70°C		WARP 23.27 % WEFT 33.94 %
Breaking strength	ISO 1421	
└ Original		WARP 96.60 daN/5cm WEFT 173.30 daN/5cm
└ After climatic chamber -30°C		WARP 97.40 daN/5cm WEFT 173.10 daN/5cm
└ After climatic chamber +70°C		WARP 94.70 daN/5cm WEFT 175.20 daN/5cm