

Natté 300		Technical info
Composition		Fibreglass 36% - PVC 64%
Openness factor	NBN EN 410	10.00%
Weight	NF EN 12127	330.00 g/m ²
Thickness	ISO 5084	0.30 mm
Density	ISO 7211/2	WARP 18.00 yarn/cm WEFT 18.00 yarn/cm
Color fastness to artificial light	ISO 105 B02	>7
Roll length		30 m
Cleaning		With soapy water
Confection		By heat, high frequency or ultrasonic welding
Fire classification		
└ Europe	UNE-EN 13501-1:2007	C-s3,d0
└ France	NF P92-503	M2
└ Italy	UNI 9177	Class 1
└ UK	BS 5867	C
└ USA	NFPA 701	FR
Tear strength	ISO 4674-1 methode 2	
└ Original		WARP 4.70 daN WEFT 4.90 daN
└ After climatic chamber -30°C		WARP 4.80 daN WEFT 4.90 daN
└ After climatic chamber +70°C		WARP 4.80 daN WEFT 4.90 daN
Elongation up to break	ISO 1421	
└ Original		WARP 2.70 % WEFT 2.70 %
└ After color fastness to artificial light		WARP 3.10 % WEFT 3.20 %
└ After climatic chamber -30°C		WARP 3.10 % WEFT 2.70 %
└ After climatic chamber +70°C		WARP 2.70 % WEFT 2.70 %
Breaking strength	ISO 1421	
└ Original		WARP 140.00 daN/5cm WEFT 140.00 daN/5cm
└ After color fastness to artificial light		WARP 140.00 daN/5cm WEFT 140.00 daN/5cm
└ After climatic chamber -30°C		WARP 135.00 daN/5cm WEFT 130.00 daN/5cm
└ After climatic chamber +70°C		WARP 100.00 daN/5cm WEFT 120.00 daN/5cm