

Natté 300P		Technical info	
Composition		29% Polyester + 71% PVC coated	
Openness factor	NBN EN 410	10.00%	
Weight	NF EN 12127	330.00 g/m ²	
Thickness	ISO 5084	0.35 mm	
Density	ISO 7211/2	WARP 18.00 yarn/cm	WEFT 18.00 yarn/cm
Color fastness to artificial light	ISO 105 B02	>7	
Roll length		30 m	
Cleaning		With soapy water	
Confection		By heat, high frequency or ultrasonic welding	
Fire classification			
└ Europe	UNE-EN 13501-1:2007	C-s3, d0	
└ France	NF P92-503	M1	
└ Italy	UNI 9177	Class 1	
└ Germany	DIN 4102	B1	
└ UK	BS 5867	C	
└ USA	NFPA 701	FR	
Tear strength	ISO 4674-1 method 2		
└ Original		WARP 5.20 daN	WEFT 4.50 daN
└ After climatic chamber -30°C		WARP 4.80 daN	WEFT 4.90 daN
└ After climatic chamber +70°C		WARP 4.80 daN	WEFT 4.90 daN
Elongation up to break	ISO 1421		
└ Original		WARP 24.50 %	WEFT 25.60 %
└ After ISO 4892-2, 1000 hr.		WARP 25.00 %	WEFT 23.70 %
└ After climatic chamber -30°C		WARP 3.10 %	WEFT 2.70 %
└ After climatic chamber +70°C		WARP 2.70 %	WEFT 2.70 %
Breaking strength	ISO 1421		
└ Original		WARP 146.00 daN/5cm	WEFT 129.00 daN/5cm
└ After ISO 4892-2, 1000 hr.		WARP 154.00 daN/5cm	WEFT 127.00 daN/5cm
└ After climatic chamber -30°C		WARP 135.00 daN/5cm	WEFT 130.00 daN/5cm
└ After climatic chamber +70°C		WARP 100.00 daN/5cm	WEFT 120.00 daN/5cm