

Natté 380P		Technical info
Composition		PVC-beschichtete Polyester-Faser
Openness factor	NBN EN 410	5.00%
Weight	NF EN 12127	415.00 g/m ²
Thickness	ISO 5084	0.42 mm
Density	ISO 7211/2	WARP 18.00 yarn/cm WEFT 19.00 yarn/cm
Color fastness to artificial light	ISO 105 B02	>7
Roll length		30 m
Cleaning		Mit Seifenwasser
Confection		By heat, high frequency or ultrasonic welding
Fire classification		
└ Europe	UNE-EN 13501-1:2007	B-s2,d0
└ France	NF P92-503	M2
└ Italy	UNI 9177	Class 1
└ Germany	DIN 4102	
└ Spain	UNE 13773	Clase 1
Tear strength	ISO 4674-1 methode 2	
└ Original		WARP 4.10 daN WEFT 3.65 daN
└ After climatic chamber -30°C		WARP 3.95 daN WEFT 3.80 daN
└ After climatic chamber +70°C		WARP 4.25 daN WEFT 3.65 daN
Elongation up to break	ISO 1421	
└ Original		WARP 23.50 % WEFT 20.50 %
└ After color fastness to artificial light		WARP 23.00 % WEFT 21.00 %
└ After climatic chamber -30°C		WARP 23.00 % WEFT 20.00 %
└ After climatic chamber +70°C		WARP 24.00 % WEFT 21.50 %
Breaking strength	ISO 1421	
└ Original		WARP 165.00 daN/5cm WEFT 155.00 daN/5cm
└ After color fastness to artificial light		WARP 160.00 daN/5cm WEFT 160.00 daN/5cm
└ After climatic chamber -30°C		WARP 165.00 daN/5cm WEFT 165.00 daN/5cm
└ After climatic chamber +70°C		WARP 165.00 daN/5cm WEFT 165.00 daN/5cm