

Natté 380P		Technical info	
Composition		Polyester with PVC coating	
Openness factor	NBN EN 410	5.00%	
Weight	NF EN 12127	415.00 g/m ²	
Thickness	ISO 5084	0.42 mm	
Density	ISO 7211/2	WARP 18.00 yarn/cm	WEFT 19.00 yarn/cm
Color fastness to artificial light	ISO 105 B02	>7	
Roll length		30 m	
Cleaning		With soapy water	
Confection		By heat, high frequency or ultrasonic welding	
Fire classification			
└ Europe	UNE-EN 13501-1:2007	B-s2,d0	
└ France	NF P92-503	M2	
└ Italy	UNI 9177	Class 1	
└ Germany	DIN 4102		
└ Spain	UNE 13773	Clase 1	
Tear strength	ISO 4674-1 methode 2		
└ Original		WARP 4.10 daN	WEFT 3.65 daN
└ After climatic chamber -30°C		WARP 3.95 daN	WEFT 3.80 daN
└ After climatic chamber +70°C		WARP 4.25 daN	WEFT 3.65 daN
Elongation up to break	ISO 1421		
└ Original		WARP 23.50 %	WEFT 20.50 %
└ After color fastness to artificial light		WARP 23.00 %	WEFT 21.00 %
└ After climatic chamber -30°C		WARP 23.00 %	WEFT 20.00 %
└ After climatic chamber +70°C		WARP 24.00 %	WEFT 21.50 %
Breaking strength	ISO 1421		
└ Original		WARP 165.00 daN/5cm	WEFT 155.00 daN/5cm
└ After color fastness to artificial light		WARP 160.00 daN/5cm	WEFT 160.00 daN/5cm
└ After climatic chamber -30°C		WARP 165.00 daN/5cm	WEFT 165.00 daN/5cm
└ After climatic chamber +70°C		WARP 165.00 daN/5cm	WEFT 165.00 daN/5cm