

Natté 390		Technical info	
Composition		Fibreglass 36% - PVC 64%	
Openness factor	NBN EN 410	3.00%	
Weight	NF EN 12127	390.00 g/m ²	
Thickness	ISO 5084	0.57 mm	
Density	ISO 7211/2	WARP 25.00 yarn/cm	WEFT 15.00 yarn/cm
Color fastness to artificial light	ISO 105 B02	>7	
Roll length		30 m	
Cleaning		With soapy water	
Confection		By heat, high frequency or ultrasonic welding	
Fire classification			
└ Europe	UNE-EN 13501-1:2007	C-s3, d0	
└ France	NF P92-503	M1	
└ Italy	UNI 9177	Class 1	
└ Germany	DIN 4102	B1	
└ UK	BS 5867	C	
└ USA	NFPA 701	FR	
Tear strength	ISO 4674-1 methode 2		
└ Original		WARP 8.22 daN	WEFT 4.83 daN
└ After climatic chamber -30°C		WARP 8.49 daN	WEFT 5.22 daN
└ After climatic chamber +70°C		WARP 8.09 daN	WEFT 4.90 daN
Elongation up to break	ISO 1421		
└ Original		WARP 7.05 %	WEFT 4.45 %
└ After color fastness to artificial light		WARP 7.30 %	WEFT 3.60 %
└ After climatic chamber -30°C		WARP 7.21 %	WEFT 4.33 %
└ After climatic chamber +70°C		WARP 7.15 %	WEFT 3.85 %
Breaking strength	ISO 1421		
└ Original		WARP 259.20 daN/5cm	WEFT 178.50 daN/5cm
└ After color fastness to artificial light		WARP 229.60 daN/5cm	WEFT 121.30 daN/5cm
└ After climatic chamber -30°C		WARP 252.70 daN/5cm	WEFT 174.70 daN/5cm
└ After climatic chamber +70°C		WARP 259.40 daN/5cm	WEFT 156.30 daN/5cm