

Natté 390P		Technical info	
<b>Composition</b>		29% Polyester + 71% PVC coated	
<b>Openness factor</b>	NBN EN 410	3.00%	
<b>Weight</b>	NF EN 12127	390.00 g/m <sup>2</sup>	
<b>Thickness</b>	ISO 5084	0.40 mm	
<b>Density</b>	ISO 7211/2	WARP 25.00 yarn/cm	WEFT 15.00 yarn/cm
<b>Color fastness to artificial light</b>	ISO 105 B02	>7	
<b>Roll length</b>		30 m	
<b>Cleaning</b>		With soapy water	
<b>Confection</b>		By heat, high frequency or ultrasonic welding	
<b>Fire classification</b>			
└ Europe	UNE-EN 13501-1:2007	C-s3, d0	
└ France	NF P92-503	M1	
└ Italy	UNI 9177	Class 1	
└ Germany	DIN 4102	B1	
└ UK	BS 5867	C	
└ USA	NFPA 701	FR	
<b>Tear strength</b>	ISO 4674-1 method 2		
└ Original		WARP 4.90 daN	WEFT 4.90 daN
└ After climatic chamber -30°C		WARP 8.49 daN	WEFT 5.22 daN
└ After climatic chamber +70°C		WARP 8.09 daN	WEFT 4.90 daN
<b>Elongation up to break</b>	ISO 1421		
└ Original		WARP 26.40 %	WEFT 25.30 %
└ After ISO 4892-2, 1000 hr.		WARP 26.00 %	WEFT 23.90 %
└ After climatic chamber -30°C		WARP 7.21 %	WEFT 4.33 %
└ After climatic chamber +70°C		WARP 7.15 %	WEFT 3.85 %
<b>Breaking strength</b>	ISO 1421		
└ Original		WARP 164.00 daN/5cm	WEFT 147.00 daN/5cm
└ After ISO 4892-2, 1000 hr.		WARP 159.00 daN/5cm	WEFT 155.00 daN/5cm
└ After climatic chamber -30°C		WARP 252.70 daN/5cm	WEFT 174.70 daN/5cm
└ After climatic chamber +70°C		WARP 259.40 daN/5cm	WEFT 156.30 daN/5cm