

Natté 420		Technical info	
Composition		Fibreglass 36% - PVC 64%	
Openness factor	NBN EN 410	1.00%	
Weight	NF EN 12127	420.00 g/m ²	
Thickness	ISO 5084	0.54 mm	
Density	ISO 7211/2	WARP 25.00 yarn/cm	WEFT 18.00 yarn/cm
Color fastness to artificial light	ISO 105 B02	>7	
Roll length		30 m	
Cleaning		With soapy water	
Confection		By heat, high frequency or ultrasonic welding	
Fire classification			
└ Europe	UNE-EN 13501-1:2007	C-s3,d0	
└ France	NF P92-503	M2	
└ Italy	UNI 9177	Class 1	
└ UK	BS 5867	C	
└ USA	NFPA 701	FR	
Tear strength	ISO 4674-1 methode 2		
└ Original		WARP 5.13 daN	WEFT 3.30 daN
└ After climatic chamber -30°C		WARP 5.19 daN	WEFT 3.44 daN
└ After climatic chamber +70°C		WARP 5.47 daN	WEFT 3.59 daN
Elongation up to break	ISO 1421		
└ Original		WARP 6.71 %	WEFT 4.46 %
└ After color fastness to artificial light		WARP 6.65 %	WEFT 4.35 %
└ After climatic chamber -30°C		WARP 6.93 %	WEFT 4.02 %
└ After climatic chamber +70°C		WARP 6.66 %	WEFT 3.75 %
Breaking strength	ISO 1421		
└ Original		WARP 244.10 daN/5cm	WEFT 190.90 daN/5cm
└ After color fastness to artificial light		WARP 253.80 daN/5cm	WEFT 180.00 daN/5cm
└ After climatic chamber -30°C		WARP 266.80 daN/5cm	WEFT 175.80 daN/5cm
└ After climatic chamber +70°C		WARP 244.50 daN/5cm	WEFT 162.60 daN/5cm