

Natté 420		Technical info	
<b>Composition</b>		Fibreglass 36% - PVC 64%	
<b>Openness factor</b>	NBN EN 410	1.00%	
<b>Weight</b>	NF EN 12127	420.00 g/m <sup>2</sup>	
<b>Thickness</b>	ISO 5084	0.54 mm	
<b>Density</b>	ISO 7211/2	WARP 25.00 yarn/cm	WEFT 18.00 yarn/cm
<b>Color fastness to artificial light</b>	ISO 105 B02	>7	
<b>Roll length</b>		30 m	
<b>Cleaning</b>		With soapy water	
<b>Confection</b>		By heat, high frequency or ultrasonic welding	
<b>Fire classification</b>			
└ Europe	UNE-EN 13501-1:2007	C-s3, d0	
└ France	NF P92-503	M1	
└ Italy	UNI 9177	Class 1	
└ Germany	DIN 4102	B1	
└ UK	BS 5867	C	
└ USA	NFPA 701	FR	
<b>Tear strength</b>	ISO 4674-1 methode 2		
└ Original		WARP 5.13 daN	WEFT 3.30 daN
└ After climatic chamber -30°C		WARP 5.19 daN	WEFT 3.44 daN
└ After climatic chamber +70°C		WARP 5.47 daN	WEFT 3.59 daN
<b>Elongation up to break</b>	ISO 1421		
└ Original		WARP 6.71 %	WEFT 4.46 %
└ After color fastness to artificial light		WARP 6.65 %	WEFT 4.35 %
└ After climatic chamber -30°C		WARP 6.93 %	WEFT 4.02 %
└ After climatic chamber +70°C		WARP 6.66 %	WEFT 3.75 %
<b>Breaking strength</b>	ISO 1421		
└ Original		WARP 244.10 daN/5cm	WEFT 190.90 daN/5cm
└ After color fastness to artificial light		WARP 253.80 daN/5cm	WEFT 180.00 daN/5cm
└ After climatic chamber -30°C		WARP 266.80 daN/5cm	WEFT 175.80 daN/5cm
└ After climatic chamber +70°C		WARP 244.50 daN/5cm	WEFT 162.60 daN/5cm