

Natté 420P		Technical info
Composition		29% Polyester + 71% PVC coated
Openness factor	NBN EN 410	1.00%
Weight	NF EN 12127	420.00 g/m ²
Thickness	ISO 5084	0.45 mm
Density	ISO 7211/2	WARP 25.00 yarn/cm WEFT 18.00 yarn/cm
Color fastness to artificial light	ISO 105 B02	>7
Roll length		30 m
Cleaning		With soapy water
Confection		By heat, high frequency or ultrasonic welding
Fire classification		
└ Europe	UNE-EN 13501-1:2007	C-s3, d0
└ France	NF P92-503	M1
└ Italy	UNI 9177	Class 1
└ Germany	DIN 4102	B1
└ UK	BS 5867	C
└ USA	NFPA 701	FR
Tear strength	ISO 4674-1 method 2	
└ Original		WARP 5.60 daN WEFT 4.00 daN
└ After climatic chamber -30°C		WARP 5.19 daN WEFT 3.44 daN
└ After climatic chamber +70°C		WARP 5.47 daN WEFT 3.59 daN
Elongation up to break	ISO 1421	
└ Original		WARP 27.20 % WEFT 22.20 %
└ After ISO 4892-2, 1000 hr.		WARP 26.10 % WEFT 21.10 %
└ After climatic chamber -30°C		WARP 6.93 % WEFT 4.02 %
└ After climatic chamber +70°C		WARP 6.66 % WEFT 3.75 %
Breaking strength	ISO 1421	
└ Original		WARP 185.30 daN/5cm WEFT 129.80 daN/5cm
└ After ISO 4892-2, 1000 hr.		WARP 191.50 daN/5cm WEFT 134.20 daN/5cm
└ After climatic chamber -30°C		WARP 266.80 daN/5cm WEFT 175.80 daN/5cm
└ After climatic chamber +70°C		WARP 244.50 daN/5cm WEFT 162.60 daN/5cm