

Natté 420P		Technical info	
Composition		PVC-beschichtete Polyester-Faser	
Openness factor	NBN EN 410	1.00%	
Weight	NF EN 12127	420.00 g/m ²	
Thickness	ISO 5084	0.45 mm	
Density	ISO 7211/2	WARP 25.00 yarn/cm	WEFT 18.00 yarn/cm
Color fastness to artificial light	ISO 105 B02	>7	
Roll length		30 m	
Cleaning		Mit Seifenwasser	
Confection		By heat, high frequency or ultrasonic welding	
Fire classification			
└ Europe	UNE-EN 13501-1:2007	B-s2,d0	
└ France	NF P92-503	M2	
└ Italy	UNI 9177	Class 1	
└ Germany	DIN 4102	B1	
└ Spain	UNE 13773	Clase 1	
Tear strength		ISO 4674-1 method 2	
└ Original		WARP 5.60 daN	WEFT 4.00 daN
└ After climatic chamber -30°C		WARP 5.19 daN	WEFT 3.44 daN
└ After climatic chamber +70°C		WARP 5.47 daN	WEFT 3.59 daN
Elongation up to break		ISO 1421	
└ Original		WARP 27.20 %	WEFT 22.20 %
└ After ISO 4892-2, 1000 hr.		WARP 26.10 %	WEFT 21.10 %
└ After climatic chamber -30°C		WARP 6.93 %	WEFT 4.02 %
└ After climatic chamber +70°C		WARP 6.66 %	WEFT 3.75 %
Breaking strength		ISO 1421	
└ Original		WARP 185.30 daN/5cm	WEFT 129.80 daN/5cm
└ After ISO 4892-2, 1000 hr.		WARP 191.50 daN/5cm	WEFT 134.20 daN/5cm
└ After climatic chamber -30°C		WARP 266.80 daN/5cm	WEFT 175.80 daN/5cm
└ After climatic chamber +70°C		WARP 244.50 daN/5cm	WEFT 162.60 daN/5cm