

Natté 420P		Technical info
<b>Composition</b>		29% Polyester + 71% PVC coated
<b>Openness factor</b>	NBN EN 410	1.00%
<b>Weight</b>	NF EN 12127	420.00 g/m <sup>2</sup>
<b>Thickness</b>	ISO 5084	0.45 mm
<b>Density</b>	ISO 7211/2	WARP 25.00 yarn/cm      WEFT 18.00 yarn/cm
<b>Color fastness to artificial light</b>	ISO 105 B02	>7
<b>Roll length</b>		30 m
<b>Cleaning</b>		With soapy water
<b>Confection</b>		By heat, high frequency or ultrasonic welding
<b>Fire classification</b>		
└ Europe	UNE-EN 13501-1:2007	B-s2,d0
└ France	NF P92-503	M2
└ Italy	UNI 9177	Class 1
└ Germany	DIN 4102	B1
└ Spain	UNE 13773	Clase 1
<b>Tear strength</b>	ISO 4674-1 method 2	
└ Original		WARP 5.60 daN      WEFT 4.00 daN
└ After climatic chamber -30°C		WARP 5.19 daN      WEFT 3.44 daN
└ After climatic chamber +70°C		WARP 5.47 daN      WEFT 3.59 daN
<b>Elongation up to break</b>	ISO 1421	
└ Original		WARP 27.20 %      WEFT 22.20 %
└ After ISO 4892-2, 1000 hr.		WARP 26.10 %      WEFT 21.10 %
└ After climatic chamber -30°C		WARP 6.93 %      WEFT 4.02 %
└ After climatic chamber +70°C		WARP 6.66 %      WEFT 3.75 %
<b>Breaking strength</b>	ISO 1421	
└ Original		WARP 185.30 daN/5cm      WEFT 129.80 daN/5cm
└ After ISO 4892-2, 1000 hr.		WARP 191.50 daN/5cm      WEFT 134.20 daN/5cm
└ After climatic chamber -30°C		WARP 266.80 daN/5cm      WEFT 175.80 daN/5cm
└ After climatic chamber +70°C		WARP 244.50 daN/5cm      WEFT 162.60 daN/5cm