



Shadow 270 - grey | white (001002)

Technical info

FRONT



BACK



Widths		This product is only made to order. Please contact us for more information.	
Composition		Fibra de vitrio 36% - PVC 64%	
Openness factor	NBN EN 410	20.00%	
Weight	NF EN 12127	285.00 g/m ²	
Thickness	ISO 5084	0.42 mm	
Density	ISO 7211/2	WARP 23.00 yarn/cm	WEFT 6.00 yarn/cm
Color fastness to artificial light	ISO 105 B02	> 7	
Roll length		50 m	
Cleaning		Con acqua saponata	
Confection		By heat, high frequency or ultrasonic welding	
Fire classification			
└ France	NF P92-503	M1	
└ Italy	UNI 9177	Class 1	
└ Germany	DIN 4102		
└ UK	BS 5867	C	
└ USA	NFPA 701	FR	

Shadow 270 - grey white (001002)		Technical info	
Tear strength	ISO 4674-1 methode 2		
↳ Original		WARP 4.30 daN	WEFT 3.60 daN
↳ After climatic chamber -30°C		WARP 5.40 daN	WEFT 3.70 daN
↳ After climatic chamber +70°C		WARP 3.70 daN	WEFT 4.50 daN
Elongation up to break	ISO 1421		
↳ Original		WARP 3.20 %	WEFT 2.10 %
↳ After color fastness to artificial light		WARP 3.20 %	WEFT 1.90 %
↳ After climatic chamber -30°C		WARP 3.80 %	WEFT 1.80 %
↳ After climatic chamber +70°C		WARP 3.00 %	WEFT 1.80 %
Breaking strength	ISO 1421		
↳ Original		WARP 135.00 daN/5cm	WEFT 50.00 daN/5cm
↳ After color fastness to artificial light		WARP 120.00 daN/5cm	WEFT 47.00 daN/5cm
↳ After climatic chamber -30°C		WARP 130.00 daN/5cm	WEFT 140.00 daN/5cm
↳ After climatic chamber +70°C		WARP 110.00 daN/5cm	WEFT 45.00 daN/5cm

Front - Interior

Shadow 270 - grey | white (001002)

Visual properties

Tv = Visual light transmittance	22.20%
Tuv = UV transmittance	20.30%

Solar energetic properties

As = Solar absorptance	57.50%
Rs = Solar reflectance	19.60%
Ts = Solar transmittance	22.80%

Fabric + glazing: G-factor

	G	Te	Qi	SC
Glazing A	0.63	0.00	0.00	0.00
Glazing B	0.61	0.00	0.00	0.00
Glazing C	0.51	0.00	0.00	0.00
Glazing D	0.29	0.00	0.00	0.00

G = Total solar energy transmittance / Te = Direct solar transmittance / Qi = Secondary heat transfer factor / SC = Shading coefficient

Back - Interior

Shadow 270 - grey | white (001002)

Visual properties

Tv = Visual light transmittance	22.20%
Tuv = UV transmittance	20.30%

Solar energetic properties

As = Solar absorptance	57.40%
Rs = Solar reflectance	19.60%
Ts = Solar transmittance	22.80%

Fabric + glazing: G-factor

	G	Te	Qi	SC
Glazing A	0.63	0.00	0.00	0.00
Glazing B	0.61	0.00	0.00	0.00
Glazing C	0.51	0.00	0.00	0.00
Glazing D	0.29	0.00	0.00	0.00

G = Total solar energy transmittance / Te = Direct solar transmittance / Qi = Secondary heat transfer factor / SC = Shading coefficient