



Déco N203 Blockout - white | sand-white
(020302)

Technical info

FRONT



BACK



| | | |
|---|---------------------|---|
| Widths | | 240 cm |
| Composition | | Déco N203 flock laminated |
| Openness factor | NBN EN 410 | 0.00% |
| Weight | NF EN 12127 | 700.00 g/m ² |
| Thickness | ISO 5084 | 0.65 mm |
| Density | ISO 7211/2 | WARP 22.00 yarn/cm WEFT 20.00 yarn/cm |
| Color fastness to artificial light | ISO 105 B02 | >7 |
| Roll length | | 30 m |
| Cleaning | | With soapy water |
| Confection | | By heat, high frequency or ultrasonic welding |
| Fire classification | | |
| └ Europe | UNE-EN 13501-1:2007 | awaiting results |
| └ France | NF P92-503 | M2 |
| └ Italy | UNI 9177 | Class 1 |
| └ Germany | DIN 4102 | B2 |
| └ UK | BS 5867 | C |
| └ USA | NFPA 701 | FR |

Déco N203 Blockout - white | sand-white
(020302)

Technical info

| | | | |
|--|----------------------|---------------------|---------------------|
| Tear strength | ISO 4674-1 methode 2 | | |
| ↳ Original | | WARP 2.90 daN | WEFT 3.10 daN |
| ↳ After climatic chamber -30°C | | WARP 2.40 daN | WEFT 2.90 daN |
| ↳ After climatic chamber +70°C | | WARP 2.70 daN | WEFT 3.40 daN |
| Elongation up to break | ISO 1421 | | |
| ↳ Original | | WARP 7.20 % | WEFT 3.50 % |
| ↳ After color fastness to artificial light | | WARP 6.10 % | WEFT 2.90 % |
| ↳ After climatic chamber -30°C | | WARP 6.30 % | WEFT 2.80 % |
| ↳ After climatic chamber +70°C | | WARP 5.10 % | WEFT 1.40 % |
| Breaking strength | ISO 1421 | | |
| ↳ Original | | WARP 185.00 daN/5cm | WEFT 200.00 daN/5cm |
| ↳ After color fastness to artificial light | | WARP 170.00 daN/5cm | WEFT 200.00 daN/5cm |
| ↳ After climatic chamber -30°C | | WARP 125.00 daN/5cm | WEFT 160.00 daN/5cm |
| ↳ After climatic chamber +70°C | | WARP 110.00 daN/5cm | WEFT 90.00 daN/5cm |

Front - Interior

 Déco N203 Blockout - white | sand-white
(020302)

Visual properties

| | |
|--|-------|
| Tv = Visual light transmittance | 0.00% |
| Tuv = UV transmittance | 0.00% |

Solar energetic properties

| | |
|---------------------------------|--------|
| As = Solar absorptance | 41.30% |
| Rs = Solar reflectance | 58.70% |
| Ts = Solar transmittance | 0.00% |

Fabric + glazing: G-factor

| | G | Te | Qi | SC |
|------------------|----------|-----------|-----------|-----------|
| Glazing A | 0.37 | 0.00 | 0.37 | 0.43 |
| Glazing B | 0.39 | 0.00 | 0.39 | 0.52 |
| Glazing C | 0.38 | 0.00 | 0.38 | 0.64 |
| Glazing D | 0.26 | 0.00 | 0.26 | 0.80 |

G = Total solar energy transmittance / Te = Direct solar transmittance / Qi = Secondary heat transfer factor / SC = Shading coefficient

Visual comfort

| | | |
|--|---------|--------------------|
| Normal solar transmittance | Class 4 | Very good effect |
| Glare control | Class 4 | Very good effect |
| Privacy night | Class 2 | Moderate effect |
| Visual contact with the outside | Class 2 | Moderate effect |
| Daylight utilisation | Class 0 | Very little effect |

Thermal comfort G-factor = Total solar energy transmittance

| Glazing A | Glazing B | Glazing C | Glazing D |
|------------------|------------------|------------------|------------------|
| Class 1 | Class 1 | Class 1 | Class 2 |

Thermal comfort Qi-factor = Secondary heat transfer factor

| Glazing A | Glazing B | Glazing C | Glazing D |
|------------------|------------------|------------------|------------------|
| Class 0 | Class 0 | Class 0 | Class 1 |

Class 0 = Very little effect / 1 = Little effect / 2 = Moderate effect / 3 = Good effect / 4 = Very good effect

Back - Interior

 Déco N203 Blockout - white | sand-white
(020302)

Visual properties

| | |
|--|-------|
| Tv = Visual light transmittance | 0.00% |
| Tuv = UV transmittance | 0.00% |

Solar energetic properties

| | |
|---------------------------------|--------|
| As = Solar absorptance | 32.80% |
| Rs = Solar reflectance | 67.20% |
| Ts = Solar transmittance | 0.00% |

Fabric + glazing: G-factor

| | G | Te | Qi | SC |
|------------------|----------|-----------|-----------|-----------|
| Glazing A | 0.32 | 0.00 | 0.32 | 0.38 |
| Glazing B | 0.35 | 0.00 | 0.35 | 0.46 |
| Glazing C | 0.35 | 0.00 | 0.35 | 0.59 |
| Glazing D | 0.25 | 0.00 | 0.25 | 0.77 |

G = Total solar energy transmittance / Te = Direct solar transmittance / Qi = Secondary heat transfer factor / SC = Shading coefficient

Visual comfort

| | | |
|--|---------|--------------------|
| Normal solar transmittance | Class 4 | Very good effect |
| Glare control | Class 4 | Very good effect |
| Privacy night | Class 2 | Moderate effect |
| Visual contact with the outside | Class 2 | Moderate effect |
| Daylight utilisation | Class 0 | Very little effect |

Thermal comfort G-factor = Total solar energy transmittance

| Glazing A | Glazing B | Glazing C | Glazing D |
|------------------|------------------|------------------|------------------|
| Class 2 | Class 2 | Class 2 | Class 2 |

Thermal comfort Qi-factor = Secondary heat transfer factor

| Glazing A | Glazing B | Glazing C | Glazing D |
|------------------|------------------|------------------|------------------|
| Class 0 | Class 0 | Class 0 | Class 1 |

Class 0 = Very little effect / 1 = Little effect / 2 = Moderate effect / 3 = Good effect / 4 = Very good effect