

Opac 400 Classic - linen (015015)

Technical info

FRONT



BACK



Widths		200 cm 300 cm
Composition		Fabric of vinyl laminated glassfibre
Openness factor	NBN EN 410	0.00%
Weight	NF EN 12127	432.00 g/m ²
Thickness	ISO 5084	0.34 mm
Color fastness to artificial light	ISO 105 B02	7
Roll length		30 m
Cleaning		With soapy water
Confection		By heat, high frequency or ultrasonic welding
Fire classification		
└ France	NF P92-503	M2
└ Italy	UNI 9177	Class 1
└ Spain	UNE 13773	Clase 1

Opac 400 Classic - linen (015015)		Technical info	
Tear strength	ISO 4674-1 method 2		
└ Original		WARP 6.90 daN	WEFT 6.30 daN
└ After climatic chamber -30°C		WARP 5.60 daN	WEFT 5.30 daN
└ After climatic chamber +70°C		WARP 6.70 daN	WEFT 5.30 daN
Elongation up to break	ISO 1421		
└ Original		WARP 3.90 %	WEFT 3.74 %
└ After color fastness to artificial light		WARP 3.17 %	WEFT 3.26 %
└ After climatic chamber -30°C		WARP 3.48 %	WEFT 4.24 %
└ After climatic chamber +70°C		WARP 4.32 %	WEFT 4.16 %
Breaking strength	ISO 1421		
└ Original		WARP 168.60 daN/5cm	WEFT 201.30 daN/5cm
└ After color fastness to artificial light		WARP 94.10 daN/5cm	WEFT 105.50 daN/5cm
└ After climatic chamber -30°C		WARP 151.70 daN/5cm	WEFT 221.10 daN/5cm
└ After climatic chamber +70°C		WARP 182.80 daN/5cm	WEFT 223.90 daN/5cm

Front - Interior

Opac 400 Classic - linen (015015)

Visual properties

Tv = Visual light transmittance	0.00%
Tuv = UV transmittance	0.00%

Solar energetic properties

As = Solar absorptance	38.70%
Rs = Solar reflectance	61.30%
Ts = Solar transmittance	0.00%

Fabric + glazing: G-factor

	G	Te	Qi	SC
Glazing A	0.35	0.00	0.35	0.42
Glazing B	0.38	0.00	0.38	0.50
Glazing C	0.37	0.00	0.37	0.62
Glazing D	0.25	0.00	0.25	0.79

G = Total solar energy transmittance / Te = Direct solar transmittance / Qi = Secondary heat transfer factor / SC = Shading coefficient

Visual comfort

Normal solar transmittance	Class 4	Very good effect
Glare control	Class 4	Very good effect
Privacy night	Class 2	Moderate effect
Visual contact with the outside	Class 2	Moderate effect
Daylight utilisation	Class 0	Very little effect

Thermal comfort G-factor = Total solar energy transmittance

Glazing A	Glazing B	Glazing C	Glazing D
Class 1	Class 1	Class 1	Class 2

Thermal comfort Qi-factor = Secondary heat transfer factor

Glazing A	Glazing B	Glazing C	Glazing D
Class 0	Class 0	Class 0	Class 1

Class 0 = Very little effect / 1 = Little effect / 2 = Moderate effect / 3 = Good effect / 4 = Very good effect

Back - Interior

Opac 400 Classic - linen (015015)

Visual properties	
Tv = Visual light transmittance	0.00%
Tuv = UV transmittance	0.00%

Solar energetic properties	
As = Solar absorptance	38.30%
Rs = Solar reflectance	61.70%
Ts = Solar transmittance	0.00%

Fabric + glazing: G-factor				
	G	Te	Qi	SC
Glazing A	0.35	0.00	0.35	0.41
Glazing B	0.38	0.00	0.38	0.50
Glazing C	0.37	0.00	0.37	0.62
Glazing D	0.25	0.00	0.25	0.79

G = Total solar energy transmittance / Te = Direct solar transmittance / Qi = Secondary heat transfer factor / SC = Shading coefficient

Visual comfort		
Normal solar transmittance	Class 4	Very good effect
Glare control	Class 4	Very good effect
Privacy night	Class 2	Moderate effect
Visual contact with the outside	Class 2	Moderate effect
Daylight utilisation	Class 0	Very little effect

Thermal comfort G-factor = Total solar energy transmittance			
Glazing A	Glazing B	Glazing C	Glazing D
Class 1	Class 1	Class 1	Class 2

Thermal comfort Qi-factor = Secondary heat transfer factor			
Glazing A	Glazing B	Glazing C	Glazing D
Class 0	Class 0	Class 0	Class 1

Class 0 = Very little effect / 1 = Little effect / 2 = Moderate effect / 3 = Good effect / 4 = Very good effect