

Opac 400 Classic - linen		Technical info
FRONT		BACK
Widths		This product is only made to order. Please contact us for more information.
Composition		Fabric of vinyl laminated glassfibre
Openness factor	NBN EN 410	0.00%
Weight	NF EN 12127	432.00 g/m ²
Thickness	ISO 5084	0.34 mm
Color fastness to artificial light	ISO 105 B02	7
Roll length		30 m
Cleaning		With soapy water
Confection		By heat, high frequency or ultrasonic welding
Fire classification		
└ France	NF P92-503	M2
└ Italy	UNI 9177	Class 1
└ Spain	UNE 13773	Clase 1

Opac 400 Classic - linen		Technical info	
Tear strength	ISO 4674-1 method 2		
↳ Original		WARP 6.90 daN	WEFT 6.30 daN
↳ After climatic chamber -30°C		WARP 5.60 daN	WEFT 5.30 daN
↳ After climatic chamber +70°C		WARP 6.70 daN	WEFT 5.30 daN
Elongation up to break	ISO 1421		
↳ Original		WARP 3.90 %	WEFT 3.74 %
↳ After color fastness to artificial light		WARP 3.17 %	WEFT 3.26 %
↳ After climatic chamber -30°C		WARP 3.48 %	WEFT 4.24 %
↳ After climatic chamber +70°C		WARP 4.32 %	WEFT 4.16 %
Breaking strength	ISO 1421		
↳ Original		WARP 168.60 daN/5cm	WEFT 201.30 daN/5cm
↳ After color fastness to artificial light		WARP 94.10 daN/5cm	WEFT 105.50 daN/5cm
↳ After climatic chamber -30°C		WARP 151.70 daN/5cm	WEFT 221.10 daN/5cm
↳ After climatic chamber +70°C		WARP 182.80 daN/5cm	WEFT 223.90 daN/5cm